

TABLE 5.

Industry-Product Analysis—Summary of Industry Shipments and Receipts and Net Shipments of Primary Products: 1963 and 1958

(In thousands of dollars)									
Ind. code	Industry and year	Value of shipments and receipts of establishments classified in the industry					Value of net shipments of primary products of the industry shipped by establishments in all industries		
		Total	Primary products	Secondary products	Receipts for services	Products purchased and resold without further processing	Total (in industry in all industries)	Produced in this industry	Produced in other industries
1051	Bauxite, 1958					(D)			
1062	Manganese ores 1963	21,491	(D)				20,478	20,478	
1063	Tungsten ores and ferroalloy ores, 1958	18,174	18,155	(D)	19		17,355	17,355	
1064 1963	7,228	(D)	(D)			804	804	
1069 1958	39,385	(D)	(D)	(D)		32,776	(D)	(D)
		83,476	(D)	(D)	(D)		100,652	(D)	(D)
		72,136	(D)	(D)	(D)		81,543	(D)	(D)
(NA) Not available. (X) Not applicable. Standard Notes: - Represents zero. (D) Withheld to avoid disclosing figures for individual companies.									
Includes the value of purchases for resale.									

TABLE 6A.

Primary Products of the Industry: 1963 and 1958

1963					1958				
Quantity (1,000 long tons)		Shipments including interplant transfers or receipts			Production (1,000 long tons)		Shipments including interplant transfers or receipts		
Item	Production (1,000 long tons)	Dried bauxite equivalent (1,000 long tons)	Value (\$1,000)		Item	Production (1,000 long tons)	Dried bauxite equivalent (1,000 long tons)	Value (\$1,000)	
BAUXITE									
Production and shipments:					Production and shipments:				
Crude (undried) bauxite:					Crude (undried) bauxite:				
Mined		1,863	(X)	(X)	Mined	1,611	(X)	(X)	(X)
Shipped to treatment plants		(3)	139	79	Shipped to treatment plants	(2)	117	1,259	14,807
Shipped to consumers		(X)	1,789	1,478	Shipped to consumers	(X)	4		
Treated bauxite, total		(59)	59	674	Treated bauxite, total	(X)	1,519	1	2,548
Dried		(D)	(D)	(D)	Dried	(1)	9	48	1,047
Calcined and activated		(D)	1963		Calcined and activated	(3)	3	1,501	
		(D)				(6)	9	8	
		(D)				(9)	3		
		(D)				(2)	4		
		(D)				(4)	4		
1958									
Value (\$1,000)		Shipments including interplant transfers or receipts			Production (1,000 long tons)		Shipments including interplant transfers or receipts		
Item	Production (1,000 long tons)	Quantity (1,000 long tons)	Value (\$1,000)		Item	Production (1,000 long tons)	Quantity (1,000 long tons)	Value (\$1,000)	
MANGANESE ORES									
Production and shipments:					Production and shipments:				
Crude manganese ores					Crude manganese ores				
.....								

percent or more manganese. . .

	(D)	(D)	1,395	508	17,448
		6,752	333	321	20 3
		6,752	9	9	83
			324	312	286
					20,09
					7
Manganese crude and treated ores treated:					
Produced and treated at same establishment	(n)	(x)	(x)	(X)	(X)
Received from other establishments for treatment.	(X)	62	4,424	493	10,675

Standard Notes: - Represents zero for individual companies. (NA) Not available. (D) Withheld to avoid disclosing figures (X) Not applicable.

The average chemical analysis, dry basis, of crude bauxite shipped in 1963 was: Al_2O_3 , 49.9 percent; SiO_2 , 14.2 percent; Fe_2O_3 , 7.4 percent; FeO , 4.7 percent; TiO_2 , 2.3 percent; loss on ignition, 26.2 percent. The average free moisture in crude bauxite shipped was 16.3 percent.

Not shown to avoid disclosing figures for kaolin shipped as a secondary product by 4 bauxite establishments.

For 1963, the quantity of crude or dried bauxite received from other establishments for treatment or mined and treated in the same establishment, was 234 thousand long tons.